

DEGADUR® 526

Middle-viscous methacrylate resin for manufacturing of 2-component topcoats for wet areas, mainly in the food industry.

Properties

Clear or pigmented topcoat particularly for broadcast or trowel applied DEGADUR® BODY COAT resins coatings mainly for production areas in the food industry with increased loading of water and fat. DEGADUR® 526 shows the following improved properties:

- good self levelling
- low yellowing
- improved hot water and fat resistance up to 80 °C

Application

In order to achieve best curing it is necessary to apply DEGADUR® 526 with a minimum thickness of about 0.4 mm (400 g/m²) each workstep. To ensure the right slip-resistance and to avoid yellowing and flaking a maximum of about 0.8 mm (800 g/m²) should be applied.

The total quantity of catalysed DEGADUR® 526 is completely poured onto the coating and distributed by means of a rubber blade if the surface is smooth. In case of broadcast surfaces the rubber blade should be finely serrated (3 mm teeth).

Best results are achieved on smooth surfaces with a subsequently use of a short-hair roller (Mohair, 4 mm pile woven). However, it is recommended to use Polyamid-roller with 12 mm pile woven onto broadcast surfaces.

Pigment-powder amount of 5 - 10 % by wt. is possible. During the time stirring in the pigment-powder the temperature should not exceed 35 °C. The shelf life of pigmented topcoats is limited and must be tested.

Pot life and hardening time at different temperatures:

Temperature [°C]**)	Hardener [% by wt.]*)	Pot life [min] ***)	Hardening time [min]
5 - 10	1.5	approx. 75	approx. 80
10 - 20	1.5	approx. 35	approx.45
20 - 25	1.0	approx. 18	approx. 35
> 25	1.0	approx. 15	approx. 25

*) Quantity calculated on DEGADUR® 526.

***) Temperature statements refer to resin-, floor- and air-temperature.

****) The indication of the approximate pot life always refers to the lower temperature.

Note: All values are derived from laboratory tests. Deviations caused by environmental factors might occur.

More accounts

DEGADUR® 526 top coats should not be applied on DEGADUR® 332 coatings since small hair cracks might appear due to the extreme difference in flexibility between base coat and the hard topcoat.

To avoid yellowing the hardener quantities must be kept as shown in the table. Use efficient air ventilation in order to provide a safe surface curing. Due to the thermoplastic character of MMA-coatings black tire-marks (skid marks) can appear from forklift trucks.


Evonik Resource Efficiency GmbH
 Rodenbacher Chaussee 4
 63457 Hanau-Wolfgang
 Germany
 PHONE +49 6181 59-4028
 FAX +49 6181 59-4919

Evonik Degussa Corporation
 299 Jefferson Road
 Parsippany,
 NJ 07054 USA
 PHONE +001 973 929-8000

Evonik Degussa (China) Co., Ltd.
 55 Chundong Road,
 Xinzhuang Industry Park
 Shanghai 201108, China
 PHONE +86 21 61191-027
 FAX +86 21 61191-534

Product Information
 21.03.2018
 T DEGADUR 526 e
 Page 1/2

DEGADUR® 526



This product has been awarded with an certified Environmental Product Declaration according to ISO 14025. This declaration describes the specific environmental performance of building products listed herein and supports the development of environmentally and health friendly buildings. The validated declaration authorizes the use of the sign of the Institut Bauen und Umwelt e.V.

Typical properties are approximate reference values. If you need product specifications please contact us.

® = registered trademark

DEGADUR is a registered trademark of Evonik Röhm GmbH, Darmstadt, Germany.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.