

DEGADUR® 332

Higher-viscous, elasticized methacrylate resin for manufacturing of broadcast 2-component floorcoatings on concrete and metal surfaces as well as asphalt-applications indoors.

Typical properties

Property	Value	Unit	Method
Form supplied	Slightly turbid liquid		
Viscosity at 23 °C	669 - 1,003	mPas	Brookfield DV2, sp. 2/12 rpm
Density at 20 °C	0.98	g/cm ³	DIN 51757
T _{max} at 23 °C	16 - 23 min /		20.0 g DEGADUR® 332 +
	85 - 125 °C		0.4 g BPO 50%
Flash point	10	°C	MMA, DIN 51755

General remarks

Activator	DEGADUR® 332 is preactivated for temperatures from 5 °C to 30 °C.		
Initiator/Hardener	BPO-Hardener (50 %), depending on temperature		
Shelf life	at ≤ 25 °C minimum 12 months in original containers / from date of delivery		
	at \leq 30 °C minimum 6 months in original containers / from date of delivery		
Storage	Protect against direct sunlight. At temperatures below 15 °C the paraffin dissolved in the		
	binder may precipitate. The material must be stirred thoroughly before use.		
Packaging	Steel drum, 200 kg net		
More accounts	see technical data sheet DEGADUR® 332		
	This product contains max. 30 g/l residual volatiles (ASTM 2369 Method E).		

Typical properties are approximate reference values. If you need product specifications please contact us.

DEGADUR is a registered trademark of Evonik Röhm GmbH, Darmstadt, Germany.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Resource Efficiency GmbH

Rodenbacher Chaussee 4 63457 Hanau-Wolfgang Germany

PHONE +49 6181 59-4028 Fax +49 6181 59-4919

Evonik Degussa Corporation Evonik Degussa (China) Co., Ltd. 299 Jefferson Road Parsippany, NJ 07054 USA PHONE +001 973 929-8000

55 Chundong Road, Xinzhuang Industry Park Shanghai 201108, China PHONE +86 21 61191-027 Fax +86 21 61191-534

Product Information 27.02.2018 P DEGADUR 332 e Page 1/1