



# Rhino™ 1346

## White, Thixotropic Gel Epoxy Resin

### Data Sheet



ISO 9001:2000  
FM62236

#### DESCRIPTION:

White, highly thixotropic rigid epoxy resin with excellent physical properties. Very high resin viscosity for high build applications or repairs. Holds heavy tooling fabrics in place during cure. 100% solids, highly resistant to crystallization, Zero VOCs and DOT non-regulated.

#### SUGGESTED USES:

Overhead work, general purpose repairs, adhesives and “coving” applications (with 3146 GEL hardener). Used where a white color is desired.

#### PROPERTIES OF RHINO 1346 Gel RESIN (neat):

Viscosity:	Highly Thixotropic Paste
EEW:	189 – 192
Color:	White
Weight/Gal:	9.7 – 9.8lbs

#### MIXING:

Recommend Rhino 1346 Gel be used between 65° – 85°F (product and ambient temperatures). Use below 45°F requires special hardener selection, consult with Rhino sales personnel for low temperature recommendations. Remove all surface contaminants such as water, dirt, rust, and petroleum products. Mold surfaces must be waxed or otherwise “released” prior to epoxy application. All Rhino curing agents are compatible with Rhino 1346 Gel so proportion resin and hardener in accordance with the selected Rhino hardener. Mix resin and hardener for 3-5 minutes being certain to scrape the bottom and sides of the mixing container. Mix no material than may be applied before the expiration of the pot life.

#### CURING:

Rhino 1346 GEL cures overnight at typical ambient temperatures (65° – 85°F) with full properties developing in 7 days, see hardener data for specific cure schedules and properties.

#### HOW SUPPLIED:

45lb Pails only (net weights). FOB San Diego, CA.

#### SAFETY PRECAUTIONS:

**Health Considerations: Consult the Rhino Linings® Material Safety Data Sheets.**

This chemical system requires the use of proper safety equipment and procedures. Please follow the Rhino Linings® product MSDS and Safety Manual for detailed information and handling guidelines.

#### For Your Protection:

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning the products and their uses, applications, storage and handling are only the opinion of Rhino Linings Corporation. Users should conduct their own tests to determine the suitability of these products for their own particular purposes and of the storage and handling methods herein suggested. The toxicity and risk characteristics of products made by Rhino Linings Corporation will necessarily differ from the toxicity and risk characteristics developed when such products are used with other materials during a manufacturing process. The resulting risk characteristics should be determined and made known to ultimate end-users and processors. Because of numerous factors affecting results, **Rhino Linings Corporation makes no warranty of any kind, express or implied**, other than that the material conforms to its applicable current Standard Specifications. Rhino Linings Corporation hereby disclaims any and all other warranties, including but not limited to those of merchantability or fitness for a particular purpose. No statements made herein may be construed as a representation or warranty. The liability of Rhino Linings Corporation for any claims arising from or sounding in breach of warranty, negligence, strict liability, or otherwise shall be limited to the purchase price of the material.

©2009 Rhino Linings Corporation. All rights reserved.

Resin - Rhino™ 1346



**Rhino Linings Corporation**  
9151 Rehco Road, San Diego, CA 92121  
858-450-0441 • Fax 858-450-6881  
1-800-422-2603  
www.rhinolinings.com

Rhino Linings Australasia Pty Ltd ..... +61 7 5585 7000  
(Asia and Australia)  
Rhino Linings Canada, Inc ..... 1-866-447-1471  
Rhino Linings Europe ..... +49 6103 936474  
(Africa, Europe and Middle East)  
Rhino Linings Latin America..... +52 55 5632 0195  
(Mexico, Caribbean, Central and South America)

5513 081409