



RhinoSpeed BPO Hardener

Hardener quantity for RhinoSpeed resins with regard to temperature

	40 - 50 °F 4 - 10 °C (fl.oz/gal)	50 - 60 °F 10 - 15 °C (fl.oz/gal)	60 - 70 °F 15 - 21 °C (fl.oz/gal)	70 - 80 °F 21 - 26 °C (fl.oz/gal)	80 - 90 °F 26 - 32 °C (fl.oz/gal)	> 90 °F > 32 °C (fl.oz/gal)
RhinoSpeed DP	4	3	2.5	1	1.5	1.5
RhinoSpeed SP	10	8	7	6	5	4
RhinoSpeed AP	10	8	7	6	5	4
RhinoSpeed FB	10	8	6	4	4	2
RhinoSpeed SB	9	6	5	4	3	2
RhinoSpeed MB	10	8	6	4	4	2
RhinoSpeed SS	3.5	3	2.5	1.5	1.5	1.5
RhinoSpeed FS	7	5	4	3	2	2

1 - Peroxide quantity calculated on used resin. Temperature remondendations refer to resin, floor and air temperature.

2 - Quantity calculated on RhinoSpeed DP include the RhinoSpeed DP Filler

Note: All values are derived from laboratory tests. Deviations caused by environmental factors might occur.



Flooring Headquarters, 9747 Businesspark Ave, San Diego, CA 92131, USA

T: +1 858 450 0441 | E: info@rhinoflooring.com | Toll Free: 800 422 2603

www.rhinoflooring.com